CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Sub Division, BBMP
Name of Work	Construction of CC road to Widening portion cross roads at western side of Kodigehalli layout Ward No. 02 of Yelahanka Sub Division
Name of Agency	Sri. T. C. Shankaregowda
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	Sample-1	18/01/2015	15/02/2015	28	8.19	490	**21.78**	**21.78**
2					8.20	495	22.00	
3					8.18	485	21.56	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Gangalore - 560027
Ph: 080 - 4114 7867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Sub Division, BBMP
Name of Work	Construction of CC road to Widening portion cross roads at western side of hemlapura Layout Ward No. 02 of Yelahanka Sub Division.
Name of Agency	Sri. T.C. Shanthappa.
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (kN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	Sample-2	18/01/2015	15/02/2015	28	8.21	500	22.22	21.93
2					8.19	495	22.00	
3					8.14	485	21.56	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore – 560027
Ph: 080 – 4114 2667, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & address of the Customer	AEE, Yelahanka Sub Division, BBMP
Name of Work	Construction of CC road to Widening portion cross roads at western side of bandapura bound Ward No. 02 of Yelahanka Sub Division.
Name of Agency	Sri. T. C Shanthappa
Grade of Concrete	M-30
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	Sample-1	21/01/2015	18/02/2015	28	8.21	705	31.33	30.96
2					8.19	695	30.89	
3					8.18	690	30.67	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test submitted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Sub Division, BBMP
Name of Work	Construction of CC road to Widening portion cross roads at western side of bridge(Second West) Ward No. 02 of Yelahanka Sub Division
Name of Agency	Sri. T. C. Shankarappa
Grade of Concrete	M-30
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	Sample-2	21/01/2015	18/02/2015	28	8.39	700	31.11	31.19
2					8.38	695	30.89	
3					8.20	710	31.56	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the Lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

AEE

CIVIL TECH LABS
#5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Sub Division, BBMP
Name of Work	Construction of CC road to Widening portion cross roads at western side of kodigepa layout Ward No. 02 of Yelahanka Sub Division.
Name of Agency	Sri. T. G. Shankarappa
Grade of Concrete	M-30
No. of cubes tested	3
Dimension of Specimen	150mm x 150mm x 150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	Sample-1	21/01/2015	18/02/2015	28	8.22	715	31.78	31.41
2					8.19	700	31.11	
3					8.20	705	31.33	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full without the written approval of the lab.
3. Any corrections invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE